Technical Data Sheet



PF CC 201 (HGW 2082)

Phenolic resin pressed paper

General properties	Unit	Norm	Guideline value
Bulk density	g / cm³	(1,3 - 1,4)	1,3 - 1,4
Water absorption at 3mm thickness	mg	249	249
Mechanical properties			
Flexural strength	MPa	100	130 - 140
Impact strength	kJ/m²	-	30
Notched impact strength (Charpy) parallelto the layer direction	kJ/m²	8,8	9 - 10
Tensile strength	MPa	(80)	80
Compressive strength parallel to the layer	(МРа	-	170
Splitting force	N	-	2500
Modulus of elasticity bending test	MPa	(7000)	7000
Shear strength parallel to the layer direction	r MPa	(25)	60
Thermal properties			
Thermal conductivity	W / (m * K)	-	0,2
Coefficient of linear expansion	10 ⁻⁶ /K	-	20-40
Limit temperature	°C	(120)	110 - 120
Limit value determination of the limit temperature due to the bending strength	MPa	-	65
Heat class		-	А
Glow resistance	Stage	-	2b
Electrical properties			
Insulation resistance	ΜΩ	1	1
Dielectric constant		-	5
Tracking resistance	CTI	100	100
Dielectric strength (1-minute test stress) at 90°C parallel to the coating direction	kV	1	1
Dielectric strength (1-minute test stress) at 90°C perpendicular to the coating direction.	kV/mm	0,5	1-1,6

The values in () are characteristic values given for information only; they must not be regarded as a requirement of this standard. The test values given are mean values which are backed up by ongoing statistical tests and checks. This data is purely information on quality and only leads to an assurance in the purchase contract if expressly agreed. The European Union Directive 2011/65/EU on the restriction and use of certain hazardous substances in electrical and electronic equipment (RoHS) came into force on January 27, 2011. These are the following substances: Lead, Cadmium, HexavalentesChromium, Polybrominated Biphenyls, Polybrominated Diphenyl Ethers, Mercury. We hereby declare that all our products are produced in compliance with RoHS. We act as a downstream user (producer of articles) according to the EU Regulation 1907/2006 (REACH Regulation) of December 18, 2006. According to information from our suppliers, the materials we use do not contain any substances from the candidate list (SVHC list) of 15.06.2015 in a concentration of more than 0.1 mass%.