

Technical Data Sheet



PVC MZ colored

Polyvinylchlorid increased impact strength

General properties	Density	Unit	Guideline value
Density	DIN EN ISO 1183	g / cm ³	1,42
Flammability DIN 4102	Self-assessment without testimony	---	B1
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	55
Elongation at yield stress	DIN EN ISO 527	%	4,0
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3100
Notched impact strength	DIN EN ISO 179	kJ / m ²	8
Shore hardness	DIN EN ISO 868	scale D	82
Thermal properties			
Service temperature long term	Average	°C	-20 / +60
Mean thermal Coefficient of linear expansion	DIN EN ISO 11359-2	K ⁻¹	0,8 * 10 ⁻⁴
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	74
Electrical properties			
Surface resistivity	IEC 60093	Ω	10 ¹³
Dielectric strength	IEC 60243-1	kV / mm	34

The data are guide values for the respective material and may vary depending on the processing method and specimen production. As a rule, these are average values from measurements on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured exclusively by compression molding, the measurements are usually made on sheets 20 mm thick. Deviations are possible if sheets in these thicknesses are not available. In the case of laminated sheets, the technical characteristic values refer to the unlaminated base sheets. The data cannot be readily transferred to other product types (such as tubes, solid bars) of the same material or to the further processed products. The suitability of materials for a specific application must be checked by the processor or user. The technical characteristic values are merely a planning aid. In particular, they do not represent guaranteed properties.